

ACRYGLOSS

GLOSSY WATER-BASED ENAMEL

WATER-BASED ARCHITECTURAL PAINTS



COLORTEK®

Description

Acrygloss is a durable, 100% pure acrylic, non-yellowing, water based, interior/exterior enamel paint that dries to a glossy, ultra-smooth and tough finish.

Recommended For

To be used in place of traditional oil based glossy enamels on doors, windows & trims and wet areas.

Key Features

- Excellent flow and leveling
- Excellent chemical resistance
- Non-yellowing
- Low odor & low VOC
- Fast recoat
- Easy water wash up
- Hard wearing & chip resistant
- High Gloss

Physical Properties

Solvent Type	Waterborne	
Finish Type	Gloss Level 6, a gloss finish	70 to 85 units at 60 degrees
Gloss Values	(60) = 77	Based on ASTM D523
Spreading Rate	Approximately 5-7 m ² /Kg	Depending on surface porosity and application techniques
Average Dry Time	Touch-dry in 10 minutes	Based on ASTM D 1640
Recoat	2 hours	
Flash Point	Not Applicable	
Dry Film Thickness	35 microns	
Recommended Wet Film Thickness	100 microns	
Thinner	None required (add up to 5% of clean water if required)	
Adhesion	4B	Based on ASTM D3359
UV resistance	Passes 8 hours UVA and UVB at 60°C	ASTM G154
Scrub Resistance	Higher than 10,000 cycles	Based on ASTM D2486
Dirt Pickup resistance	High dirt pickup resistance	ASTM D3719
Contrast ratio (dry opacity)	93.9% ±0.3 at 100 micron WFT 97.5% ±0.3 at 200 micron WFT	ASTM D2805
Density	1.26 g/cm ³	
Solids	47% (weight) 35% (volume)	
Storner Viscosity	100 ±5 KU at 25 °C	
Brookfield Viscosity	2000 – 5000 cP	(Spindle 3/ speed 10) at 25 °C
VOC	Maximum of 30 g/L. Testing Methods Used • ASTM D6886 • EPA Method 24(ASTM D2369) • ASTM D3960 • UL 2821 • ISO 11890-2	<ul style="list-style-type: none">• Compliant with GS-11 Standards, 1993• Compliant with UL 2818 - 2013 Gold Standard• Compliant with LEED 2009• Compliant with LEED V4• Compliant with EU Directive 2004/42/EC• Compliant with SCAQMD Rule 1113, 2004• Compliant with California Department of Public Health (CDPH) Standard Method V1.1-2010
Bases	None	
Colors	Pure White	

ACRYGLOSS

GLOSSY WATER-BASED ENAMEL

WATER-BASED ARCHITECTURAL PAINTS



COLORTEK®

Certifications & Compliance

THIS PRODUCT IS GREENGUARD GOLD CERTIFIED

The above-mentioned certification determines our products compliance with the following building codes and programs amongst others:

- CHPS 2.2.2 : Paints & Coatings; LEED 2008, LEED 2009 and LEED V4

This product is compliant with the following standards

- Masters Paint Institute #114 – Latex, Interior, Gloss (MPI Gloss Level 6)
- Masters Paint Institute #119 – Latex, Exterior, Gloss (MPI Gloss Level 6)
- Masters Paint Institute #154 – Light Industrial Coating, Interior, Water Based, Gloss (MPI Gloss Level 6)
- Masters Paint Institute #164 – Light Industrial Coating, Exterior, Water Based, Gloss (MPI Gloss Level 6)
- GS 11

Surface Preparation

All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or any other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean and primed with a suitable Colortek primer. New plaster or masonry surfaces must be allowed to cure (28 days) before applying base coat. Cured plaster should be hard, have a slight sheen and a maximum pH of 10. A soft, porous or powdery plaster indicates improper cure. Knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles.

CAUTION: Scraping or sanding surfaces of older buildings may release dust containing lead or asbestos. **EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH.** Always wear appropriate personal protective equipment during surface preparation and finish cleanup of any residues by water-washing all surfaces.

Primer Systems

SURFACE TYPE	RECOMMENDED COLORTEK PRIMER
Drywall	Colortek Primer
Porous masonry	Colortek Sealer
Non-porous masonry	Colortek Primer or Colortek Undercoat
Wood	Colortek Undercoat
Ferrous metal	SX47 StopRust or Colortek Adhero

Application Conditions

Do not apply at temperatures below 5 °C or when rain is expected. Stir well. Apply using brush, roller or airless spray.

Pack Size

- 1 US Gallon – 4 kg
- 1 US Quart – 1 kg

Shelf Life

24 months from the date of production.

Storage and Handling

Care should be taken to avoid spillage. Store in a dry area. Protect from freezing. Extreme temperatures may cause paint to become unusable. For example: freezing and thawing may cause paint to gel, and high heat may cause solid skin to form.

Safety

Use under well ventilated conditions. Avoid skin contact. In case of eye contact, flush immediately with water for at least 15 minutes and seek medical attention immediately. If you have trouble breathing, leave the area to obtain fresh air and seek medical attention immediately.

ACRYGLOSS

GLOSSY WATER-BASED ENAMEL

WATER-BASED ARCHITECTURAL PAINTS



Cleaning

Remove as much leftover product as possible from the application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Do not empty product into drains or watercourses.

Technical Assistance

Available through your local COLORTEK® Design Center or through your COLORTEK PAINTS® authorized distributor. For the location of the retailer nearest you, email us at info@colortek.eu or check our website www.colortek.eu.

Disclaimer

Product batches are subject to stringent quality control checks in conformity with ISO 9001:2008, Certificate CH12/1128. The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.