



## Description

Aurora® is a crystal inspired product composed of genuine precision-cut SWAROVSKI® crystals especially designed to give interior architects access to an indispensable material for today's renowned international designers, ensuring their creations push the boundaries of imagination.

Aurora comes with 22 500 SWAROVSKI ELEMENTS per gallon.

## Recommended For

Interior & exterior applications on plaster, embossed wall coverings, gypsum board, concrete, cement rendering, brickwork & block work.

## Key Features

- Creates a flawless facet that refracts light
- Sparkles endlessly
- Durable, tough film development
- Specially coated crystals for Excellent water repellency and scrub resistance
- Odorless
- Non-flammable
- Thermal insulating properties
- Aids in acoustical insulation

## Physical Properties

<b>Solvent Type</b>	Waterborne
<b>Finish Type</b>	Textured light refractive glimmer finish
<b>Spreading Rate</b>	1.25 kg/m <sup>2</sup> depending on surface porosity and application technique
<b>Average Dry Time</b>	1 hour based on ASTM D 1640
<b>Recoat</b>	After 2 - 4 hours, recoat as needed
<b>Flash Point</b>	Not Applicable
<b>Dry Film Thickness</b>	700 - 850 microns
<b>Thinner</b>	No thinning needed
<b>Solids</b>	Greater than 70 %
<b>Viscosity</b>	80,000 - 120,000 cP (Spindle 7/Speed 10) based on ASTM D2196
<b>VOC</b>	Very low VOC content - Compliant with EU 2010 regulations maximum of 30 g/L.

## Surface Preparation

All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or any other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth, dusted clean and primed with a suitable Colortek primer.

New plaster or masonry surfaces must be allowed to cure (28 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure. Knife off any protrusions and prime the plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles.

**CAUTION:** Scraping or sanding surfaces of older buildings may release dust containing lead or asbestos. **EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH.** Always wear appropriate personal protective equipment during surface preparation and finish clean-up of any residues by water-washing all surfaces.



## Primer Systems

SURFACE TYPE	RECOMMENDED COLORTEK PRIMER
Drywall	Colortek Primer, Colortek Fondo T
Porous masonry	Colortek Sealer, Colortek Primer, Colortek Fondo T
Non-porous masonry	Colortek Primer or Colortek Undercoat, Colortek Fondo T
Wood	Colortek Undercoat, Colortek Fondo T
Ferrous metal	Colortek Adhero, Colortek Fondo T
Non-ferrous metal	Colortek Adhero, Colortek Fondo T

## Application Conditions

Do not apply at temperatures below 5 °C or when rain is expected.

## Application Method

- Apply COLORTEK FONDO T as a primer, tinted to match Aurora color by textured roll. wait until 50 % dry before applying 2<sup>nd</sup> hand trowel without materials ( to smooth up the primer )
- AURORA is applied using an Inox trowel. Spread evenly across the primed surface to create an evenly distributed surface.

## Pack Size

- 1 US Quart – 1 kg
- 1 US Gallon – 2.5 kg

## Shelf Life

24 months from the date of production.

## Storage and Handling

Care should be taken to avoid spillage. Store in a dry area. Protect from freezing. Extreme temperatures may cause paint to become unusable. For example: freezing and thawing may cause paint to gel, and high heat may cause solid skin to form.

## Safety

Use under well ventilated conditions. Do not breathe or inhale spray mist or sanding dust. Avoid skin contact; spillage on the skin should immediately be removed with suitable cleanser, soap and water. In case of eye contact, flush immediately with water for at least 15 minutes and seek medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

## Cleaning

Remove as much leftover product as possible from the application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Do not empty product into drains or watercourses.

## Technical Assistance

Available through your local COLORTEK® Design Center or through your COLORTEK PAINTS® authorized distributor. For the location of the retailer nearest you, email us at [info@colortek.eu](mailto:info@colortek.eu) or check our website [www.colortek.eu](http://www.colortek.eu).

## Disclaimer

Product batches are subject to stringent quality control checks in conformity with ISO 9001:2008, Certificate CH12/1128.

The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.